

POLYMER SOLUTIONS

EOS TPU 1301

Material Data Sheet

EOS TPU 1301

Product Description

The part properties such as flexibility and level of damping can be adjusted via structural design with lattice structure, or by adapting the process parameters. With a reusability rate of 80 % EOS TPU 1301 is a highly efficient thermoplastic elastomer contributing to lower cost per part, less material waste and a reduced powder carbon footprint.

MAIN CHARACTERISTICS

- Great resilience
- Good hydrolysis resistance
- High UV-stability
- Very good shock absorption
- Shore hardness 86 A
- Low refresh rate

TYPICAL APPLICATIONS

- Footwear & lifestyle parts that demand elastomeric properties, e. g. handles, shoe soles
- Automotive & industry parts, e.g. tubes, bellows, seals, gaskets
- Protective sports gear, e.g. helmet cushioning
- Applications usually made from foam can be replaced by lattice structures in EOS TPU 1301

MECHANICAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Tensile Modulus			ISO 527-1/-2
X Orientation	60 / -	MPa	
Y Orientation	60 / -	MPa	
Z Orientation	60 / -	MPa	
Tensile Strength			ISO 527-1/-2
X Orientation	7 / -	MPa	
Y Orientation	7 / -	MPa	
Z Orientation	5 / -	MPa	
Strain at Break			ISO 527-1/-2
X Orientation	250 / -	%	
Y Orientation	250 / -	%	
Z Orientation	90 / -	%	
Strain at Break, EOS P 770			ISO 527-1/-2
Z Orientation	60 / -	%	
Flexural Modulus			ISO 178
X Orientation	64 / -	MPa	
Y Orientation	64 / -	MPa	
Z Orientation	69 / -	MPa	
Charpy Impact Strength (+23°C)			ISO 179/1eU
X Orientation	N / -	kJ/m ²	
Y Orientation	N / -	kJ/m ²	
Z Orientation	N / -	kJ/m ²	
Charpy Notched Impact Strength (+23°C)			ISO 179/1eA
X Orientation	N / -	kJ/m ²	
Y Orientation	N / -	kJ/m ²	
Z Orientation	N / -	kJ/m ²	
Charpy Notched Impact Strength (-30°C)			ISO 179/1eA
X Orientation	N / -	kJ/m ²	
Y Orientation	N / -	kJ/m ²	
Z Orientation	N / -	kJ/m ²	
Rebound Resilience			DIN 53512
X Orientation	62 / -	%	
Y Orientation	62 / -	%	
Z Orientation	62 / -	%	
Abrasion Resistance			ISO 4649
X Orientation	86 / -	mm ³	
Z Orientation	95 / -	mm ³	
Compression Set			ISO 815-1/B (24h 70°C 30 m
X Orientation	65 / -	%	
Z Orientation	72 / -	%	

THERMAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Melting Temperature	138	°C	ISO 11357-1/-3
Temperature of Deflection under Load 0.45 MPa			ISO 75-1/-2
X Orientation	50	°C	
Z Orientation	52	°C	
Vicat Softening Temperature			ISO 306/A120
X Orientation	98	°C	
Z Orientation	98	°C	

OTHER PROPERTIES	VALUE	UNIT	TEST STANDARD
Water Absorption	0.85	%	sim. to ISO 62/7d
Density	1.11	g/cm ³	EOS Method
Powder Color	white	-	-
Components Color	white	-	-

HEADQUARTERS

EOS GmbH Electro Optical Systems	Robert-Stirling-Ring 1 82152 Krailling / Munich Germany	Tel.: +49 89 893 36-0 Email: info@eos.info URL: www.eos.info
---	---	--

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.